

**Product Code:**

117-2410	Matte
117-2420	Low Gloss
117-2435	Satin
117-2450	Semi-Gloss
117-2490	High Gloss

<b>VISCOSITY:</b>	Zahn #3 signature cup 24 sec at 77°F
<b>FLASH POINT:</b>	55°F (12.8°C)
<b>DENSITY (lb/gal):</b>	9.42
<b>SOLID (% by weight):</b>	58.6%
<b>SOLID (% by volume):</b>	43.5%
<b>SHELF LIFE (months):</b>	12

**Product Description:** Chemlife 24 White is an acid curing, light stable, fast drying Reactive Amino Coating (RAC) with good building properties. It gives a smooth, knock-proof and hardwearing surface resisting influence from alcohol, water, etc. Due to its 24 hour pot-life, Chemlife 24 White provides the customer with minimum waste resulting in lower production costs. It also provides very good light stability based on the type of resin used and superior vertical hang.

Special Recognition: When applied as specified, will meet required performance for the ANSI/KCMA A161.1 1990 9.0 Finish Test. Recommended: Architectural Woodwork Institute (AWI) O.P.4.

**Uses:** This product is used as the final coat over wood, plywood, chipboard, etc., meant for interior use. This product is recommended for kitchen cabinets, high build office or residential furniture as well as many other interior wood applications where high build and durability are required.

**Environmental Data (as supplied):**

<b>VOC less exempt lb/gal:</b>	<3.90
<b>VOC lb/gal:</b>	<3.90
<b>VOC less exempt g/l:</b>	<468
<b>VOC g/l:</b>	<468
<b>VOC lb/lb Solid:</b>	<0.75
<b>VHAPs lb/lb Solid:</b>	<0.30

See individual compliance sheets for specific data

<b>Application Data:</b>	<b>SUGGESTED USES:</b>	Wood Finish
	<b>MIXING RATIO:</b>	10 parts 117-24XX to 1 part 873-1251
	<b>POT LIFE:</b>	24 hours
	<b>APPLICATION VISCOSITY:</b>	Zahn #2 signature cup 22 – 25 seconds
	<b>REDUCER:</b>	803-1325
	<b>RETARDER:</b>	800-5328
	<b>CLEAN-UP SOLVENT:</b>	803-1298
	<b>RECOMMENDED WET FILM:</b>	4-5 mils
	<b>COVERAGE:</b>	698 sq. ft/gal at 1 mil dry and at 100% transfer efficiency. Coverage will vary depending on method of application or coating thickness.

## Directions for Use

Chemlife® 24 White Pigmented Post-Cat TC  
117-24XX

**Surface Preparation:** Primer should be sanded using 240 and 320 grit steared paper. Suitable primer is Chemlife 24 White Primer 522-2400. The Primer should be topcoated within eight hours of sanding. Care should be taken during sanding to avoid sanding through the primer.

**General information:** Catalyze and reduce the material as recommended. Chemlife 24 White is applied in one or two coats and can be used on all kinds of wood meant for interior use.

A thorough sanding between the coats is essential to the adhesion. The second and subsequent coats must be applied the same day as the previous coat is sanded. Chemlife 24 White cannot be used on metal, old oil or cellulose lacquers.

Total recommended film build of Chemlife 24 White Primer 522-2400 and Chemlife 24 White 117-24XX is not to exceed 6 mils dry. Over the primer, the topcoat should not exceed 4 mils dry.

To ensure proper sheen, the catalyzed material should be agitated at all times. Chemlife 24 White must be thoroughly stirred while adding catalyst and thinner in the recommended mixing ratio. Contact with metal surfaces should be avoided once the Chemlife 24 White has been catalyzed.

Chemlife 24 White must not be polluted with oil, varnish or the like and must not be sanded with steel wool between coats. Chemlife 24 White must not be used and dried at temperatures below 65°F (18°C) or relative humidity above 65%. During the curing process, the coating must not be exposed to ammonia vapors. Ammonia cleaners should not be used for cleaning the finished surface. This may accelerate discoloration.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION.

### Drying Times:

	Room Temperature (68°F)	Forced Drying Schedule (122°F)
<b>Tack Free Time:</b>	15 – 20 minutes	Flash off before entering oven
<b>Dry to Sand:</b>	3 hours	1 hour
<b>Dry to Stack:</b>	Overnight	3 hours

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F (18°C) must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc  
1431 Progress Ave  
High Point, NC 27260  
336-841-5111

**DISTRIBUTED BY:**  
**Pro Wood Finishes**  
**14622 Southlawn Lane**  
**Rockville MD 20850**  
**Ph: (301) 424-3033**