



Technical Data Sheet

Product	KKR1 Sheen/Series		
Description	Polyurethane pigmented matt converters		
Colour	White		
Chemical-physical Properties			
CODE	Density (Kg/l)	Density (lb/US gal)	Solid content %
KKR1	1,300 ± 0,030	10,8 ± 0,3	66,6 ± 2
KKR2	1,300 ± 0,030	10,8 ± 0,3	64,6 ± 2
KKR01	1,250 ± 0,030	10,4 ± 0,3	64,2 ± 2
(series average values)	Viscosity (EN ISO 2431) ISO 6 cup	90 ± 5	
USAGE INDICATIONS			
Complementary products			
Hardner	LNB77	In weight w/w %	50
		In volume v/v %	68
	Solid content %	23,4 ± 2	
Thinner	LZC8643	In weight w/w %	30
		In volume v/v %	46
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
	Solid content I + II component (%)	51,5 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h	
	Viscosity (Ford 4 cup)	20 ± 2	
Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron: 140	
		Wet Mils: 5,5	
	KKR1	Sheen 20 ± 2	
	KKR2	Sheen 10 ± 1	
	KKR01	Sheen 50 ± 1	
Application	Application system	Quantities	
	Hand spray	gr/m ² min-max: 130 - 160	
		Wet Mils min-max 4,7 - 5,7	
PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		8 h
	Dust free		10 min
	Touch dry		30 min
	Hard dry		12 h



Complementary products			
Properties	Excellent yellowing resistance and drying speed		
Hardner	LNB20	In weight w/w %	50
		In volume v/v %	68
	Solid content %	25,0 ± 2	
Thinner	LZC8643	In weight w/w %	30
		In volume v/v %	46
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
	Solid content I + II component (%)	52,1 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h	
	Viscosity (Ford 4 cup)	20 ± 2	
Code/ Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron: 140	
		Wet Mills: 5,5	
	KKR1	Sheen	22 ± 2
	KKR2	Sheen	12 ± 1
	KKR01	Sheen	54 ± 1
Application	Application system	Quantities	
	Hand spray	gr/m ² min-max:	130 - 160
		Wet Mills min-max	4,7 - 5,7
PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		6 h
	Dust free		10 min
	Touch dry		30 min
	Hard dry		12 h
Complementary products			
Properties	Excellent yellowing resistance		
Hardner	LNB18	In weight w/w %	50
		In volume v/v %	67
	Solid content %	26,2 ± 2	
Thinner	LZC8643	In weight w/w %	30
		In volume v/v %	46



READY TO USE PRODUCT PROPERTIES (AVERAGE)		
	Solid content I + II component (%)	52,5 ± 2
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h
	Viscosity (Ford 4 cup)	20 ± 2
Code/ Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)
		applied micron: 140
		Wet Mils: 5,5
	KKR1	Sheen 21 ± 2
	KKR2	Sheen 11 ± 1
KKR01	Sheen 52 ± 1	
Application	Application system	Quantities
	Hand spray	gr/m ² min-max: 130 - 160
		Wet Mils min-max 4,7 - 5,7
PRODUCT PROPERTIES AFTER APPLICATION		
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	
	8 h	
	Dust free	
	10 min	
	Touch dry	
30 min		
Hard dry		
12 h		
Shelf life	12 months after production	



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 2014-04

**DISTRIBUTED BY:
Pro Wood Finishes
14622 Southlawn Lane
Rockville MD 20850
Ph: (301) 424-3033**