



## Technical Data Sheet

<b>Product</b>	<b>LBR102</b>		
<b>Description</b>	Polyurethane pigmented primer		
<b>Color</b>	White		
<b>Woods for which the product is suitable</b>	Resinous softwood		
	Non resinous softwood		
	Light color hardwood		
	Dark color hardwood		
<b>Substrates for which the product is suitable</b>	Solid wood		
	MDF (Medium Density Fiberboard)		
<b>Chemical-physical Properties</b>	Density (Kg/l)	1,351	± 0,030
	Density (lb/US gal)	11,3	± 0,3
	Solid content %	71,6	± 2
	Viscosity (Ford 8 cup)	20	± 2
<b>USAGE INDICATIONS</b>			
<b>Additional products</b>	<b>Quantities</b>		
<b>Hardener</b>	LNB77	In weight w/w %	50
		In volume v/v %	70,1
	Solid content %	23,4	± 2
<b>Thinner</b>	LZC1026	In weight w/w %	20
		In volume v/v %	31
<b>READY TO USE PRODUCT PROPERTIES</b>			
	Solid content 1st + 2nd component (%)	55,5	± 2
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	2 h	
	Viscosity (Ford 4 cup)	20	± 2
<b>Application</b>	<b>Application method</b>	<b>Quantities</b>	
	Electrostatic spray	gr/m <sup>2</sup> min-max:	130 - 150
		Wet Mils min-max	4,5 - 5,2
	Hand spray	gr/m <sup>2</sup> min-max:	130 - 150
Wet Mils min-max		4,5 - 5,2	



PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying ( 18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	24 h	
	Dust free	10 min	
	Touch dry	30 min	
	Hard dry	12 h	
	Stackable after room temperature drying	24 h	
	Sandable after (time)	4 h	
	Overcoatability time	20-24 h	
	Overcoatability time between layers	2 h	
	Maximum time between layers without sanding	3 h	
	Additional products		Quantities
Properties	Excellent elasticity and filling power		
Hardener	LNB613	In weight w/w %	40
		In volume v/v %	55,3
	Solid content %	26,1 ± 2	
Thinner	LZC1026	In weight w/w %	20
		In volume v/v %	31
READY TO USE PRODUCT PROPERTIES			
	Solid content 1st + 2nd component (%)	58,6 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	4 h	
	Viscosity (Ford 4 cup)	20 ± 2	
Application	Application method	Quantities	
	Electrostatic spray	gr/m <sup>2</sup> min-max:	130 - 150
		Wet Mils min-max	4,4 - 5,1
	Hand spray	gr/m <sup>2</sup> min-max:	130 - 150
Wet Mils min-max		4,4 - 5,1	



PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying ( 18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	24 h	
	Dust free	10 min	
	Touch dry	30 min	
	Hard dry	12 h	
	Stackable after room temperature drying	24 h	
	Sandable after (time)	4 h	
	Overcoatability time	20-24 h	
	Overcoatability time between layers	2 h	
	Maximum time between layers without sanding	3 h	
	Additional products		Quantities
Properties	Excellent yellowing resistance		
Hardener	LNB190	In weight w/w %	50
		In volume v/v %	70,7
	Solid content %	26,2 ± 2	
Thinner	LZC1026	In weight w/w %	20
		In volume v/v %	31
READY TO USE PRODUCT PROPERTIES			
	Solid content 1st + 2nd component (%)	56,5 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	2 h	
	Viscosity (Ford 4 cup)	20 ± 2	
Application	Application method	Quantities	
	Electrostatic spray	gr/m <sup>2</sup> min-max:	130 - 150
		Wet Mils min-max	4,5 - 5,2
	Hand spray	gr/m <sup>2</sup> min-max:	130 - 150
Wet Mils min-max		4,5 - 5,2	



PRODUCT PROPERTIES AFTER APPLICATION		
Drying	Room temperature drying ( 18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	24 h
	Dust free	10 min
	Touch dry	30 min
	Hard dry	12 h
	Stackable after room temperature drying	24 h
	Sandable after (time)	4 h
	Overcoatability time	20-24 h
	Overcoatability time between layers	2 h
	Maximum time between layers without sanding	3 h
	Shelf life	18 months after production



### WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

**Issue date:** 2014-05



## Technical Data Sheet

<b>Product</b>	<b>LBR90</b>		
<b>Description</b>	Polyurethane pigmented basecoat		
<b>Color</b>	Black		
<b>Woods for which the product is suitable</b>	Light color hardwood		
	Dark color hardwood		
	Non resinous softwood		
	Resinous softwood		
<b>Substrates for which the product is suitable</b>	Solid wood		
	Veneer		
	MDF (Medium Density Fiberboard)		
<b>Chemical-physical Properties</b>	Density (Kg/l)	1,210	± 0,030
	Density (lb/US gal)	10,1	± 0,3
	Solid content %	66,5	± 2
	Viscosity (Ford 6 cup)	33	± 3
<b>USAGE INDICATIONS</b>			
<b>Additional products</b>		<b>Quantities</b>	
<b>Hardener</b>	<b>LNB77</b>	In weight w/w %	50
		In volume v/v %	62,8
	Solid content %	23,4	± 2
<b>Thinner</b>	<b>LZC1026</b>	In weight w/w %	20
		In volume v/v %	28
<b>READY TO USE PRODUCT PROPERTIES</b>			
	Solid content 1st + 2nd component (%)	52,1	± 2
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	2 h	
	Viscosity (Ford 4 cup)	20	± 2
<b>Application</b>	<b>Application method</b>	<b>Quantities</b>	
	<b>Electrostatic spray</b>	gr/m <sup>2</sup> min-max:	120 - 140
		Wet Mils min-max	4,4 - 5,1
	<b>Hand spray</b>	gr/m <sup>2</sup> min-max:	120 - 140
Wet Mils min-max		4,4 - 5,1	



PRODUCT PROPERTIES AFTER APPLICATION			
Drying	Room temperature drying ( 18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	24 h	
	Dust free	10 min	
	Touch dry	30 min	
	Hard dry	12 h	
	Sandable after (time)	4 h	
	Overcoatability time	24 h	
	Overcoatability time between layers	1 h	
	Maximum time between layers without sanding	4 h	
	Additional products		Quantities
Properties	Excellent elasticity and filling power		
Hardener	LNB613	In weight w/w %	40
		In volume v/v %	49,5
	Solid content %	26,1 ± 2	
Thinner	LZC1026	In weight w/w %	20
		In volume v/v %	28
READY TO USE PRODUCT PROPERTIES			
	Solid content 1st + 2nd component (%)	55,0 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h	
	Viscosity (Ford 4 cup)	20 ± 2	
Application	Application method	Quantities	
	Electrostatic spray	gr/m <sup>2</sup> min-max:	120 - 140
		Wet Mils min-max	4,3 - 5,0
	Hand spray	gr/m <sup>2</sup> min-max:	120 - 140
Wet Mils min-max		4,3 - 5,0	



PRODUCT PROPERTIES AFTER APPLICATION		
<b>Drying</b>	Room temperature drying ( 18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	24 h
	Dust free	10 min
	Touch dry	30 min
	Hard dry	12 h
	Sandable after (time)	4 h
	Overcoatability time	24 h
	Overcoatability time between layers	1 h
	Maximum time between layers without sanding	4 h
	<b>Shelf life</b>	<b>18 months after production</b>





### WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

**Issue date:** 2014-03