



**System Three Resins, Inc.**  
 3500 W. VALLEY HWY. N. SUITE 105  
 AUBURN, WASHINGTON 98001  
 TECHNICAL SUPPORT: 253-333-8118

**DISTRIBUTED BY:**  
**Pro Wood Finishes**  
**14622 Southlawn Lane**  
**Rockville MD 20850**  
**Ph: (301) 424-3033**

**TECHNICAL DATA SHEET**

**RotFix™**  
**Epoxy Wood Sealer**  
**& Consolidant**

**DESCRIPTION:**

RotFix is a 2-component, solvent-free, low-viscosity epoxy resin sealer. RotFix, easily applied by brush or roller, seals rotted or unrotted wood, with a waterproof barrier. It penetrates deep into deteriorated and rotted wood, creating a strong, solid base for restoration. To restore the dimension of original wood shape, use System Three Sculpwood Putty or Paste. Sculpwood Putty is a kneadable, moldable, epoxy putty, while the Paste is a spreadable, frosting-like putty. After curing, they can be finished like the original wood. Together they make a high-quality, permanent wood restoration system. RotFix is an essential component of the EndRot® System.

NOTE: RotFix does not kill rot fungus or keep it from returning. For long-term protection from rot and decay, as well as from certain boring insects, use Board Defense® or Impel® Rods, available wherever the System Three products are sold.

**RESIN PROPERTIES:**

Viscosity @ 25° C ..... 300 cps  
 Specific Gravity ..... 1.10  
 Color ..... Clear

**HARDENER PROPERTIES:**

Viscosity @ 25° C ..... 400 cps  
 Specific Gravity ..... 1.03  
 Color ..... Amber

**MIXED SYSTEM PROPERTIES:**

Mix ratio by volume resin/hardener ..... 100:50  
 Mix ratio by weight resin/hardener ..... 100:43  
 Working time @ 25° C (100 grams) ..... 30 min.  
 Cure time @ 25° C ..... 8 hours

**TYPICAL CURED PROPERTIES:**

Hardness ,Shore D (24 hr. cure @ 25°C) ..... 75  
 Elongation, % ..... 8-10  
 Minimum application temperature ..... 45°F

RotFix is available in the following sizes (kits):

12 oz., 24 oz, 48 oz.

For health and safety information concerning this product, please refer to the MSDS for RotFix.

The information contained herein is based on the data available to us and is believed to be correct. However, System Three Resins, Inc. makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. System Three assumes no responsibility for injury from the use of the product described herein. System Three is a registered trademark of System Three Resins, Inc.

**Helping you put it all together**